Mar. 4. 2005 10:44AM

## EUROPEAN PATENT OFFICE No. 0453

## Patent Abstracts of Japan

PUBLICATION NUMBER

02099657

RECEIVED

PUBLICATION DATE

11-04-90

**CENTRAL FAX CENTER** 

APPLICATION DATE

07-08-89

MAR 0 4 2005

**APPLICATION NUMBER** 

: 01204551

APPLICANT: OWENS CORNING FIBERGLASS CORP;

INVENTOR: ZURSTRASSEN EDOUARD;

INT.CL.

: D04H 1/60 D04H 1/42 // B29C 67/14 B29K103:04 B29K105:08

TITLE

: PREFORMABLE MAT

ABSTRACT : PURPOSE: To obtain a preforable mat suitable for preforming a complicated shape by applying a specific thermoplastic binder to a mat formed from a glass fiber material having a specified fiber length and a mixed specific wt.%, heat-treating the resultant mat and then cooling and solidifying the heat-treated mat.

> CONSTITUTION: This preformable mat is obtained by applying forming size to a glass fiber material, chopping the resultant glass fiber material, mixing 40 wt.% of the cut material having 10.16 cm fiber length with 60 wt.% of the cut material having 15.24 cm fiber length, forming the mat, then applying a thermoplastic binder using an emulsion containing 55 wt.% of a mixture of equal amounts of a styrene-soluble polyester resin powder and a polystyrene resin powder and 45 wt.% of a polyvinyl acetate mowlith D-50 plasticized with 3% of polyethylene glycol ester adipate to the formed mat, subsequently heat- treating the formed mat at 250°C, surrounding the glass fiber material with the binder, then cooling the mat and solidifying the thermoplastic binder.

COPYRIGHT: (C)1990,JPO